

Please type a plus sign (+) inside this box →

Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PTO/SB/05 (4/08/05)
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCEA
1091/677502
10/02/00

UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))

Attorney Docket No.	0694-134
First Inventor or Application Identifier	Yoshio Hashibe
Title	Fire-Protection Glass Panel With a Heat Shielding...
Express Mail Label No.	EL467166250US

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents.

- Fee Transmittal Form (e.g., PTO/SB/17)
(Submit an original and a duplicate for fee processing)
- Specification [Total Pages **12**]
(preferred arrangement set forth below)
 - Descriptive title of the Invention
 - Cross References to Related Applications
 - Statement Regarding Fed sponsored R & D
 - Reference to Microfiche Appendix
 - Background of the Invention
 - Brief Summary of the Invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
- Drawing(s) (35 U.S.C. 113) [Total Sheets **2**]
- Oath or Declaration [Total Pages **2**]
 - Newly executed (original or copy)
 - Copy from a prior application (37 C.F.R. § 1.63(d))
(for continuation/divisional with Box 16 completed)
 - DELETION OF INVENTOR(S)
Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).

***NOTE FOR ITEMS 1 & 15: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C.F.R. § 1.27), EXCEPT IF ONE FILED IN A PROPER FEE PAYMENT (SECTION 15 RELEIVED UPON 37 C.F.R. § 1.69).**

- If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment:
 Continuation Divisional Continuation-in-part (CIP)
 of prior application No: _____
 Group / Art Unit: _____

Prior application information: Examiner: _____
For CONTINUATION or DIVISIONAL APPS only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

17. CORRESPONDENCE ADDRESS

<input type="checkbox"/> Customer Number or Bar Code Label	(Insert Customer No. or Attach bar code label here)			<input checked="" type="checkbox"/> Correspondence address below	
Name	Hopgood, Calimafde, Kalil & Judlowe, L.L.P.				
Address	60 East 42nd Street				
City	New York	State	NY	Zip Code	10165
Country	USA	Telephone	(212) 551-5000	Fax	(212) 949-2795
Name (Print/Type)	Bradley N. Ruben	Registration No. (Attorney/Agent)	32,058		
Signature			Date	10/2/2000	

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

FIRE-PROTECTION GLASS PANEL WITH
A HEAT SHIELDING CHARACTERISTIC

Background of the Invention:

The present invention relates to a fire-protection glass product such as a glass panel for use as a building material to prevent spread and expansion of fire and to assure the safety during escape from fire and, in particular, to a fire-protection glass product having a heat shielding characteristic.

As a glass product called a fire-protection glass, a wire glass, a tempered glass, and a crystallized glass are known and already put into practical use. Such fire-protection glass has heat resistance and not only serves to shield flames and smokes upon occurrence of fire but also serves as a transparent window for assuring an inside view. However, the fireproof glass can not substantially attenuate heat radiation towards an unburnt area. Such heat radiation may cause the spread of fire to a next room and the difficulty in assuring a safe escape route.

In order to shield the heat radiation, proposal has been made of a fire-protection glass product having a multilayer structure comprising two glass plates 1a and 1b with a gel layer 5 interposed therebetween as illustrated in Fig. 1. Upon occurrence of fire, the gel layer 5 foams, i.e., produces bubbles to exhibit a heat shielding characteristic.

However, the above-mentioned fire-protection glass product uses a large amount of a gel material so that a high material cost is required. In addition, since the above-mentioned glass product is large in thickness and heavy in weight, a high construction cost is also required. Moreover, upon

occurrence of fire, the gel layer foams in several minutes to become opaque. This means that the function of assuring the inside view as the transparent window can not substantially be expected.

Summary of the Invention:

It is therefore an object of the present invention to provide a fire-protection glass product which has both fireproof and heat shielding characteristics, which is light in weight and small in thickness to be easily equipped, and which does not require a gel layer.

According to one aspect of the present invention, a fire-protection glass product having a heat shielding characteristic comprises a plurality of fireproof glass plates, a resin intermediate layer interposed therebetween, and a heat-ray reflection film or IR reflection film formed on the surface of at least one of said glass plates. The heat-ray reflection film has a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays.

At least one of the fireproof glass plates may be made of a heat-resistant transparent crystallized glass.

In the fire-protection glass product according to this invention, the heat-ray reflection film, which is transparent, is formed on one or both of opposite surfaces of at least one fireproof glass plates. With this structure, heat rays produced upon occurrence of fire are reflected by the heat-ray reflection film to suppress heat emission and to attenuate heat radiation to the next room. Furthermore, a resin material used as the intermediate layer is darkened by temperature rise upon occurrence of fire and absorbs the heat rays. At usual times, the fire-protection glass product of this invention serves as a safety glass by provision of the intermediate layer which prevents shattering or scattering of cracked glass pieces when the glass product is damaged or broken by collision or impact.

The heat-ray reflection film has a reflectance of 70% or more for a light of a wavelength of 2500nm. Upon occurrence of fire, the temperature of a burnt area falls within a range between 800°C and 900°C. At this time, an energy distribution of the heat ray radiated therefrom corresponds to a light of a wavelength of 2000 to 3000nm. If the heat-ray reflectance is 70% or more for a light of the wavelength of 2500nm, the heat-ray reflection film reflects the heat radiation upon occurrence of fire and sufficiently suppresses heat radiation into the unburnt area. On the other hand, if the heat-ray reflectance is 70% or less for a light of the wavelength of 2500nm, the heat-ray reflection film cannot substantially attenuate the heat radiation so that heat-shielding characteristic is insufficient. The heat-ray reflection film has such a spectral characteristic or a light selectivity that it has reflectance of 70% or more, 50% or more, and 80% or more for spectra lights of wavelengths of 2500nm, 1500nm and 3000nm, respectively.

The heat-ray reflection film has an average transmittance of 60% or more for visible rays (400nm to 700nm). If the average transmittance for the visible rays is less than 60%, light transparency of the film is so low so that a sufficient range of view or sight cannot be assured through the glass panel with the film. This deteriorates the function of the glass panel as a window. Preferably, the heat-ray reflection film has an average reflectance of 15% or less for visible rays.

As the heat-ray reflection film having the above-mentioned characteristics, use is most preferably made of an indium oxide film containing tin, an antimony oxide film containing tin, a tin oxide film containing fluoride, or a tin oxide film containing antimony. Alternatively, a ZnO-based transparent film can also be used. These films can be deposited on the glass plate by sputtering, spraying, dipping, or the like.

The heat-ray reflection film has a thickness between 1000Å and 15000Å. If the thickness is not greater than 1000Å, the heat-ray reflectance at the wavelength of 2500nm tends to fall within the range not greater than 70%. If the thickness is not smaller than 15000Å, the average transmittance for visible rays tends to fall within the range not greater than 60%.

As the fireproof glass plate, use may be made of a low-expansion crystallized glass, a borosilicate glass, a strengthened glass, and the like, alone or in combination. In particular, the low-expansion crystallized glass is preferable as the glass plate because it is resistant against the fire continuing for a longer time period and does not break even if it is spayed water by a sprinkler.

Upon occurrence of fire, the resin intermediate layer serves to absorb heat rays because the resin material is carbonized (blackened) by incomplete combustion. At normal times, the resin intermediate layer serves to assure the safety by preventing the release and the drop of the glass pieces when the glass plate is broken. As the resin material, use may be made of fluorocarbon resin, polycarbonate resin, polyethylene terephthalate resin, and the like.

In order to achieve a higher heat shielding characteristic, the fire-protection glass product may have a double-glazing structure including an additional glass plate attached through an air layer. The fireproof glass plate may be combined with a soda-lime glass plate.

Now, embodiments of this invention will be described in detail with reference to the drawing.

Brief Description of the Drawings:

Fig. 1 is a sectional view of a conventional fire-protection glass panel having a gel layer;

Fig. 2 is a sectional view of a fire-protection glass panel according to an embodiment of this invention; and

Fig. 3 is a sectional view for describing a multilayer glass panel using the fire-protection glass panel illustrated in Fig. 2.

Description of the Preferred Embodiments:

Description will now be made as regards embodiments of this invention with reference to the drawing.

As illustrated in Fig. 2, a fire-protection glass panel having a heat shielding characteristic comprises two fireproof glass plates 1a and 1b, a resin intermediate layer 2 interposed between the glass plates 1a and 1b, and a heat-ray reflection film 3 formed on an outer surface of the fireproof glass plate 1a. The heat-ray reflection film 3 has a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays.

Referring to Fig. 3, a multi-layer glass panel comprises the fire-protection glass panel illustrated in Fig. 2 and an additional fireproof glass plate 1c with an air layer 4 interposed therebetween. This structure achieves a higher heat shielding characteristic. The fireproof glass plate may be combined with a soda-lime glass plate.

Now, specific examples of the fire-protection glass panel of this invention will be described in detail together with comparative examples.

Example 1

At first, preparation was made of two heat-resistant transparent crystallized glass plates (FIRELITE manufactured by Nippon Electric Glass Co., Ltd.) each of which has a dimension of $950 \times 600 \times 4$ mm and a thermal expansion coefficient of $-5 \times 10^{-7}/^{\circ}\text{C}$.

Subsequently, an ITO (indium-tin oxide) film was deposited onto one surface of one of the glass plates by the use of a sputtering apparatus at a temperature of 350°C. The ITO film had a thickness of 4000 Å.

Then, each glass plate was cut into a sample piece having a dimension of $900 \times 600 \times 4$ mm. Using the sample piece, the spectral characteristic of the glass plate after the above-mentioned deposition was measured by the use of a spectrophotometer. Herein, the reflectance was measured as a total internal reflectance using an integrating sphere while the transmittance was measured without using the integrating sphere.

As a result, the reflectance for a light of the wavelength of 2500nm was equal to 95% and the average transmittance for visible rays was equal to 81%. Thus, these values were preferable as external appearance of the film.

Subsequently, as a resin intermediate layer, preparation was made of a fluorocarbon resin film comprising a copolymer containing 40 weight% of tetrafluoroethylene (TFE), 20 weight% of hexafluoropropylene (HFP), and 40 weight% of vinylidene fluoride (VDF) and having a chain molecular structure. The film had a thickness of 500μ m. The resin film was placed between the fireproof glass plates and subjected to thermo-compression bonding to obtain the fire-protection glass panel as illustrated in Fig. 2. The thermo-compression bonding was carried out by holding the resin film at a predetermined temperature for 15 minutes under a pressure of 1.27MPa.

Example 2

Preparation was made of two tempered borosilicate glass plates having a dimension of $950 \times 600 \times 4$ mm, similar to that of Example 1.

Subsequently, one of the glass plates was heated by an electric furnace to a temperature of 600°C . Then, stannic chloride solution containing 1% antimony was applied onto one side surface of the above-mentioned glass plate by the use of a spraying device to deposit an antimony-containing tin oxide film. The tin oxide film thus obtained had a thickness of 2500 \AA .

In the manner similar to that mentioned in conjunction with Example 1, measurement was made of the spectral characteristic of the glass plate after

the above-mentioned deposition. As a result, the reflectance for a light of the wavelength of 2500nm was equal to 78% and the average transmittance for visible rays was equal to 74%. These values were preferable as external appearance of the film.

Thereafter, as the resin intermediate layer, preparation was made of a polyethylene terephthalate resin film having a thickness of $200\text{ }\mu\text{m}$ and having adhesive layers formed on opposite surfaces thereof. By the use of the resin film, the two glass plates were adhered to each other to obtain the fire-protection glass panel as illustrated in Fig. 2.

Comparative Example

For the purpose of comparison, preparation was made of a tempered borosilicate glass plate similar to that in Example 2.

Then, in the manner similar to Examples mentioned above, measurement was made of the spectral characteristics of the glass plate. As a result, the reflectance for a light of the wavelength of 2500nm was equal to 7% and the average transmittance for visible rays was equal to 85%.

Evaluation

Each sample of Examples 1 and 2 and Comparative Example was subjected to a heat-shielding test.

The heat-shielding test was performed in the following manner. At first, each sample was fixed to a frame at its end surfaces so as to avoid the end surfaces from being heated, and was arranged in front of a flat heating furnace. Then, the sample was heated in accordance with a standard heating curve provided in the Official Notification No.1125 of the Ministry of Construction of Japan. By the use of a heat flow sensor located at a distance of 0.5m from the center of an unheated surface of the sample, the maximum heat received thereat (W/cm^2) was measured after lapse of 60 minutes. Those samples of Examples 1 and 2 were tested for a case A in which the heat-ray reflection film

was positioned on a heated side or a side facing the heating side and a case B in which the heat-ray reflection film was positioned on the opposite or unheated side. The results are shown in Table 1.

Table 1

	Example 1	Example 2	Comparative Example
Reflectance Average for Visible Rays	12	19	6
1500nm	60	55	6
2500nm	95	78	7
3000nm	98	83	7
Transmittance Average for Visible Rays	81	74	85
1500nm	8	15	86
2500nm	3	18	87
3000nm	2	15	88
Heat Received (W/cm ²)			
Case A	1.0	1.2	3.1
Case B	1.1	1.3	-

As is obvious from Table 1, each of the Examples exhibited the heat received as low as 1.0-1.3W/cm² after lapse of 60 minutes (925°C) after start of heating. Furthermore, each of the Examples was maintained for more than about 15 minutes after start of heating to allow the other side to be seen through it.

For a conventional fire-protection glass panel (manufactured and sold by SAINT-GOBAIN CERAMIQUES IND. (FRANCE) under the trade name of CONTRAFLAM) which comprises the gel layer 5 interposed between two glass

plates 1a and 1b as illustrated in Fig. 1, the similar heat shielding test was performed. As a result, the heat received was sufficiently low but foaming of the gel layer 5 occurred so that the other side can no longer be seen through it after lapse of about 4 minutes after start of heating.

In the fire-protection glass product according to this invention, the heat radiation upon occurrence of fire is reflected by the heat-ray reflection film and absorbed by blackening of the resin layer interposed between the glass plates. Therefore, the fire-protection glass product has high heat-shielding characteristic. This suppresses the probability of combustion or ignition of matters present in a room adjacent to the fired room to thereby prevent the spread of fire. In addition, it is possible to assure a safe escape route upon occurrence of fire. Furthermore, since the light transparency can be maintained for a predetermined time duration, the status of fire can be visually confirmed to thereby facilitate lifesaving and fire fighting. Moreover, the fire-protection glass product according to this invention is thin in thickness, light in weight, and low in construction cost and is therefore advantageously used as a building material.

WHAT IS CLAIMED IS:

1. A fire-protection glass product having a heat shielding characteristic, comprising:
 - a plurality of fireproof glass plates;
 - a resin intermediate layer interposed between adjacent ones of said glass plates;
 - a heat-ray reflection film formed on the surface of at least one of said glass plates and having a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays.
2. A fire-protection glass product as claimed in claim 1, wherein at least one of said fireproof glass plates is made of a heat-resistant transparent crystallized glass.
3. A fire-protection glass product as claimed in claim 1, wherein said resin intermediate layer is made of a material selected from fluorocarbon resin, polycarbonate resin, and polyethylene terephthalate resin.
4. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film is formed on at least one of opposite surfaces of said fireproof glass plates.
5. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film is made of a material selected from indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony.
6. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film has a thickness between 1000Å and 15000Å.
7. A fire-protection glass product as claimed in claim 1, wherein said heat-ray reflection film has a reflectance of 50% or more for a light of a

wavelength of 1500nm and 80% or more for a light of a wavelength of 3000nm, and an average reflectance of 15% or less for visible rays.

8. A fire-protection glass product as claimed in claim 1, said glass product having a double-grazing structure including an additional glass plate attached through an air layer.

Abstract of the Disclosure:

A fire-protection glass product having a heat shielding characteristic comprises a plurality of fireproof glass plates, a resin intermediate layer interposed between adjacent ones of the glass plates, and a heat-ray reflection film. The heat-ray reflection film is formed on the surface of at least one of the glass plates, and has a reflectance of 70% or more for a light of the wavelength of 2500nm and an average transmittance of 60% or more for visible rays. The resin intermediate layer is made of a material selected from fluorocarbon resin, polycarbonate resin, and polyethylene terephthalate resin. At least one of the fireproof glass plates may be made of a heat-resistant transparent crystallized glass plate. The heat-ray reflection film may be formed on at least one of opposite surfaces of the fireproof glass plate. The heat-ray reflection film may be made of a material selected from indium oxide containing tin, antimony oxide containing tin, tin oxide containing fluorine, and tin oxide containing antimony. The heat ray reflection film has a thickness between 1000Å and 15000Å. The heat-ray reflection film has a reflectance of 50% or more for a light of a wavelength of 1500nm, a reflectance of 80% or more at a wavelength of 3000nm, and an average reflectance of 15% or less for visible rays.




FIG. 1




FIG. 2




FIG. 3

SOLE INVENTOR

Attorney's
Docket No. _____

DECLARATION OF INVENTORSHIP AND POWER OF ATTORNEY

As the below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below, next to my name.

I believe I am an original, first and sole inventor of the subject matter which is claimed and for which a U.S. Utility Patent is sought on the invention entitled

FIRE-PROTECTION GLASS PANEL WITH A HEAT SHIELDING CHARACTERISTIC

the specification of which

is attached hereto.
 was filed on _____ as
 Application Serial No. _____
 and was amended on _____
 (if applicable)

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims and the drawings presented therein and declare that the subject matter of the claims was part of the invention and was invented before the filing of the above-identified original application for such invention.

I hereby claim foreign priority benefits under Title 35, United States Code, §119, of any foreign patent application(s) and PCT International application(s) listed below and have also identified below any foreign patent application(s) having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)

Country	Application Number	Date of Filing	Priority Claimed
Japan	278023/1999	30 September 1999	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
_____	_____	_____	<input type="checkbox"/> [] <input type="checkbox"/> []
_____	_____	_____	<input type="checkbox"/> [] <input type="checkbox"/> []
_____	_____	_____	<input type="checkbox"/> [] <input type="checkbox"/> []

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorneys to prosecute this application and transact all business in the Patent and Trademark Office connected therewith: Hopgood, Calimafde, Kalil & Judlowe, a firm consisting of Roy C. Hopgood, Reg. No. 15,245; Eugene J. Kalil, Reg. No. 16,686; John M. Calimafde, Reg. No. 16,895; Stephen B. Judlowe, Reg. No. 21,049; Marvin N. Gordon, Reg. No. 23,094; Francis J. Murphy, Reg. No. 24,537; James M. Rhodes, Jr., Reg. No. 25,229; Dennis J. Mondolino, Reg. No. 27,148; William G. Todd, Reg. No. 28,480; Ira B. Winkler, Reg. No. 29,223; Porter F. Fleming, Reg. No. 31,759; James M. Bollinger, Reg. No. 32,555, Jae H. Kim, Reg. No. 32,907 and Brian P. Murphy, Reg. No. 34,986 at that firm.

SEND CORRESPONDENCE TO:

Mr. Jae H. Kim, Esq.

Hopgood, Calimafde et al.
60 East 42nd Street
New York, New York 10165

DIRECT TELEPHONE CALLS TO:

Mr. Jae H. Kim, Esq.

(212) 986-2480

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, §1.56(a).

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full name of first joint-inventor YOSHIO HASHIBEInventor's signature Yoshio Hashibe
Date September 26, 2000Residence Gamou-gun, Shiga, JapanCitizenship JapanesePost Office Address c/o NIPPON ELECTRIC GLASS CO., LTD., 7-1, Seiran
2-chome, Otsu-shi, Shiga 520-8639 JapanFull name of second joint-inventor AKIHIKO SAKAMOTOInventor's signature A. Sakamoto
Date September 26, 2000Residence Koka-gun, Shiga, JapanCitizenship JapanesePost Office Address c/o NIPPON ELECTRIC GLASS CO., LTD., 7-1, Seiran
2-chome, Otsu-shi, Shiga 520-8639 Japan

Full name of third joint-inventor _____

Inventor's signature _____

Date _____

Residence _____

Citizenship _____

Post Office Address _____